

(19)  Canadian
Intellectual Property
Office

An Agency of
Industry Canada

Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

(11) **CA 2 172 187** (13) **C**

(40) 19.06.2001

(43) 01.10.1996

(45) 19.06.2001

(12)

(21) 2 172 187

(51) Int. Cl. 6: **A61L 33/00, A61L 27/00,
A61L 29/00, A61M 37/00,
A61F 2/06, A61K 38/18,
A61K 38/21, A61K 47/30,
A61K 39/395, A61K 38/58**

(22) 20.03.1996

(30) 09/413,475 US 30.03.1995

(73) **ADVANCED CARDIOVASCULAR SYSTEMS, INC.**
3200 Lakeside Drive P.O. Box 58167 SANTA
CLARA XX (US).

(72) **Eury, Robert P. (US).
Garguilo, Darlene (US).
Villareal, Plaridel (US).**

(74) **SMART & BIGGAR**

(54) METHODE POUR INCORPORER DES MEDICAMENTS DANS LES COMPOSANTES POLYMERIQUES
D'EXTENSEURS

(54) METHOD OF INCORPORATING DRUGS INTO A POLYMER COMPONENT OF STENTS

(57)

The drug-loaded polymeric material containing a therapeutic drug can be applied to a structure of an intravascular stent. A therapeutically effective amount of a therapeutic drug is incorporated into such a layer of polymeric material, without significantly increasing the thickness of the stent, to avoid interfering with the function of the stent. The drug-loaded polymer coating of the stent can be formed to include pores, can be multi-layered to permit the combination of a plurality of different drug containing materials in a single stent, and can include a rate controlling membrane to allow for controlled retention and delivery of selected drugs within the affected blood vessel upon implantation. The layer of polymeric material is manufactured by combining the selected polymeric material with a relatively high loading of the therapeutic drug in a thermal process, such as coextrusion of the therapeutic drug with the polymeric material. The therapeutic drug is dispersed and incorporated into the polymer as small particles, preferably having a maximum cross-sectional dimension of 10 microns.



(22) 1996/03/20

(43) 1996/10/01

(45) 2001/06/19

(72) Eury, Robert P., US

(72) Garguilo, Darlene, US

(72) Villareal, Plaridel, US

(73) ADVANCED CARDIOVASCULAR SYSTEMS, INC., US

(51) Int.Cl.⁶ A61L 33/00, A61K 38/58, A61K 39/395, A61L 27/00,

A61M 37/00, A61L 29/00, A61K 47/30, A61K 38/21, A61K 38/18,

A61F 2/06

(30) 1995/03/30 (08/413,475) US

(54) METHODE POUR INCORPORER DES MEDICAMENTS DANS
LES COMPOSANTES POLYMERIQUES D'EXTENSEURS

(54) METHOD OF INCORPORATING DRUGS INTO A POLYMER
COMPONENT OF STENTS

(37) The drug-loaded polymeric material containing a therapeutic drug can be applied to a structure of an intravascular stent. A therapeutically effective amount of a therapeutic drug is incorporated into such a layer of polymeric material, without significantly increasing the thickness of the stent, to avoid interfering with the function of the stent. The drug-loaded polymer coating of the stent can be formed to include pores, can be multi-layered to permit the combination of a plurality of different drug containing materials in a single stent, and can include a rate controlling membrane to allow for controlled retention and delivery of selected drugs within the affected blood vessel upon implantation. The layer of polymeric material is manufactured by combining the selected polymeric material with a relatively high loading of the therapeutic drug in a thermal process, such as coextrusion of the therapeutic drug with the polymeric material. The therapeutic drug is dispersed and incorporated into the polymer as small particles, preferably having a maximum cross-sectional dimension of 10 microns.



METHOD OF INCORPORATING DRUGS
INTO A POLYMER COMPONENT OF STENTS

ABSTRACT OF THE DISCLOSURE

The drug-loaded polymeric material containing a therapeutic drug can be applied to a structure of an intravascular stent. A therapeutically effective amount of a therapeutic drug is incorporated into such a layer of polymeric material, without significantly increasing the thickness of the stent, to avoid interfering with the function of the stent. The drug-loaded polymer coating of the stent can be formed to include pores, can be multi-layered to permit the combination of a plurality of different drug containing materials in a single stent, and can include a rate controlling membrane to allow for controlled retention and delivery of selected drugs within the affected blood vessel upon implantation. The layer of polymeric material is manufactured by combining the selected polymeric material with a relatively high loading of the therapeutic drug in a thermal process, such as coextrusion of the therapeutic drug with the polymeric material. The therapeutic drug is dispersed and incorporated into the polymer as small particles, preferably having a maximum cross-sectional dimension of 10 microns.

METHOD OF INCORPORATING DRUGS
INTO A POLYMER COMPONENT OF STENTS

BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates generally to expandable intraluminal vascular grafts, generally referred to as stents and, more particularly, concerns stents coated with a polymer component capable of carrying and releasing therapeutic drugs, and a method of incorporating therapeutic drugs into the polymer component of such stents.

Description of Related Art

Systemic administration of some therapeutic pharmaceutical drugs, in order to provide an efficacious concentration of the drugs at a localized area of interest, can produce serious systemic side effects. Local administration of a therapeutic drug can be significantly more effective and produce fewer side effects than systemic delivery, particularly for anticoagulants used for preventing thrombosis of a coronary stent, and cytostatic agents applied for reducing post-angioplasty, proliferation of vascular tissue, which is a factor when restenosis occurs following an angioplasty procedure.

There thus has been a need in modern medicine for techniques for local delivery of therapeutic drugs. In one technique, catheters have been used to deliver therapeutic drugs in a solution used to bathe the tissue for a short period of time, which is effective for administration of thrombolytic drugs, or to inject the drug solution into the tissue surrounding the area of interest. However, the therapeutic effect of drugs

delivered by this method generally is relatively short, as the drugs commonly are eliminated easily from the delivery site.

5 Therapeutic drugs have been incorporated into relatively permanent structures for longer term delivery of the drugs at the site of interest. For example, extravascular wraps having a relatively large quantity of a drug in a bandage structure can be applied around the exterior of an artery. Although work in animals has
10 shown that this technique is effective for local anticoagulation with heparin, it has limited practical utility in human beings, since an invasive operation is required to place the extravascular wrap at the site of interest.

15 In another technique, coatings of therapeutic drugs have been applied to stents in order to provide sustained delivery of the drugs at the site of interest. However, coatings thick enough to provide a therapeutically effective amount of the drug can severely
20 compromise the function of the stent, and very thin coatings that do not impede the function of the stent, such as heparin coatings with a thickness of several microns, typically do not deliver a therapeutically effective amount of the drug.

25 It would be desirable to provide a method of incorporating a therapeutically effective amount of a therapeutic drug into an intravascular layer of polymeric material which can be applied to a relatively permanent intravascular device, such as a stent, that does not
30 require an invasive operation for placement of the device, in a manner that would not interfere with the functioning of the stent. The present invention meets these needs.

SUMMARY OF THE INVENTION

5 This invention provides a method of incorporating a therapeutically effective amount of a therapeutic drug into a polymeric material for application to an intravascular stent, comprising the steps of:

forming solid particles of a therapeutic drug to have a maximum cross-sectional dimension of about 10 microns;

10 uniformly dispersing the solid particles of the therapeutic drug in a polymeric material such that the particles of the therapeutic drug form greater than 30% and up to 70% by weight of the total weight of the therapeutic drug and the polymeric material;

uniformly dispersing a porosigen in the polymeric material together with the therapeutic drug; and

15 applying the polymeric material to an inner reinforcement structure to form the intravascular stent.

This invention also provides an intravascular stent for carrying and delivering a therapeutic drug within a blood vessel in which the intravascular stent is placed, comprising:

20 an inner reinforcement structure;

a polymeric material disposed on the inner reinforcement structure, the polymeric material having a relatively low thermal processing temperature and, uniformly dispersed therein, solid particles of a therapeutic drug, the solid particles of the therapeutic drug comprising greater than 30% and up to 70% by weight of the total weight of the
25 therapeutic drug and the polymeric material; and

a porosigen uniformly dispersed in the polymeric material together with the therapeutic drug.

This invention provides a polymeric material containing a therapeutic drug for application to an intravascular stent for carrying and delivering said therapeutic drug with a blood vessel in which said intravascular stent is placed, comprising:

a polymeric material having a thermal processing temperature no greater than about 100°C;

particles of a therapeutic drug incorporated in said polymeric material; and

a porosigen uniformly dispersed in said polymeric material, said porosigen being selected from the group consisting of sodium chloride, lactose, sodium heparin, polyethylene glycol, copolymers of polyethylene oxide and polypropylene oxide, and mixtures thereof. The aforementioned polymeric material may further include a rate-controlling membrane. The polymeric material may be laminated to an intravascular stent structure.

Briefly, and in general terms, the present invention provides for a polymeric material containing a
5 therapeutic drug for application to a structure of an
intravascular stent, and a method of incorporating a
therapeutically effective amount of a therapeutic drug
into a polymeric material for application to the
10 structure of an intravascular stent, which when applied
to the structure of the stent will not significantly
increase the thickness of the stent, and thus will not
interfere with the function of the stent.

Accordingly, the present invention provides for
a polymeric material containing a therapeutic drug, for
15 application to a thin reinforcement or structural member
of the stent on at least one side, for carrying and
releasing the therapeutic drug. The thin reinforcement
provides the structural strength required for maintaining
the patency of the vessel in which the stent is placed,
20 and the polymer coating provides the stent with the
capacity for carrying and releasing therapeutic drugs at
the location of the stent of the vessel in which the
stent is placed. The polymer coating can be formed to
include pores or to contain a material which will
25 dissolve or degrade to form pores in the polymeric
material, can be multi-layered to permit the combination
of a plurality of different drug containing materials in
a single stent, and can include a rate-controlling
membrane to allow for controlled retention and delivery
30 of selected drugs within the affected blood vessel upon
implantation. Depending upon the construction and
lamination of the stent, drugs can be released
simultaneously or sequentially, on the exterior surface
of the stent to a blood vessel wall, and directly into
35 the bloodstream, as desired.

The present invention also provides for a
method of incorporating a therapeutic drug into a

polymeric material. In one preferred embodiment of the method of the invention, a layer of polymeric material is manufactured by combining the selected polymeric material with a relatively high loading of the therapeutic drug in a thermal process, such as coextrusion of the therapeutic drug with the polymeric material, for example, although other thermal processes such as molding or calendaring may also be suitable. The polymeric material preferably is selected to have a relatively low processing temperature, at which the drug of interest is thermally unstable. In another preferred embodiment of the method of the invention, particularly where the drug of interest is thermally unstable and a low temperature processing polymer is not suitable, the layer of the selected polymeric material can be formed by solvent casting or by coating the polymeric material with the selected therapeutic drug. In either a thermal process, such as coextrusion, or a low or ambient temperature process, such as solvent casting, the therapeutic drug can be dispersed and incorporated into a polymer as small particles, preferably having a maximum cross-sectional dimension of about 10 microns.

These and other aspects and advantages of the invention will become apparent from the following detailed description, and the accompanying drawings, which illustrate by way of example aspects of the invention.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a cross-sectional view of an extrusion apparatus for use in combining a therapeutic drug with a polymer component of a stent according to the method of the invention;

Fig. 2 is a diagrammatic view of a laminating apparatus that can be used for laminating the

reinforcement member of the stent on one side with a drug-loaded polymeric film; and

- Fig. 3 is a diagrammatic view of a lamination apparatus that can be used for laminating the reinforcement member of the stent on two sides with a drug-loaded polymeric film.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

- Local administration of therapeutic drugs to avoid the serious side effects that can result from systemic administration of some therapeutic drugs can result in limitation of the effective duration of the drug to a relatively short period of time, due to elimination of the therapeutic drug from the delivery site. Administration of therapeutic drugs to a blood vessel by a relatively permanent intravascular device to provide a longer effective duration of localized drug therapy also poses the problem of providing a therapeutically effective amount of the drug without substantially increasing the thickness of the device, which increased thickness could injure or block the vessel when the device is deployed.

- The invention accordingly is embodied in a polymeric material containing a therapeutically effective amount of a therapeutic drug that can be combined with the reinforcement structure of an intravascular stent, and a method of incorporating the therapeutic drug into the polymeric material and forming the polymeric material as a thin layer containing a therapeutically effective amount of the therapeutic drug, to be incorporated in the stent without significantly increasing the thickness of the stent.

- As is illustrated in the drawings, in one preferred embodiment, a selected therapeutic drug is preferably intimately mixed with the selected polymeric material so as to uniformly disperse the therapeutic drug

in the polymeric material. The specific method of uniformly dispersing the therapeutic drug in the polymer can vary, and depends upon the stability of the therapeutic drug to thermal processing. However, in a preferred embodiment, the therapeutic drug is uniformly dispersed in the polymeric material by coextruding small solid particles of the selected therapeutic drug with the selected polymeric material, as is illustrated in Fig. 1. Such an extrusion apparatus 10 typically includes a hopper 12 into which the polymeric material and small particles of the selected therapeutic drug are added together, and into which a porosigen can also be added, if desired. The extruder also typically includes a lead screw 14 that drives and intimately mixes the ingredients together, to uniformly disperse the small particles of the therapeutic drug, and if desired, a porosigen as well, in the polymeric material. The barrel 16 of the extruder preferably is heated by temperature controlled heaters 18 surrounding the barrel in stages. A motor 20 and associated gears are provided to drive the lead screw, and a cooling system 22 also is typically provided. This method of intimately mixing the therapeutic drug and polymeric material can yield a relatively high and uniformly distributed loading of the therapeutic drug in the polymer. While a currently preferred loading of the therapeutic drug is no more than about 40% by weight, drug loadings as high as 70% by weight depending upon the specific application and interaction of the polymer with the drug, have been achieved by this method. The drug-loaded polymer can be extruded into an appropriate shape, or subsequently can be calendared to produce a drug-loaded polymer film having a smooth surface, with the therapeutic drug uniformly distributed in the film.

The selected therapeutic drug can, for example, be anticoagulant, antiplatelet or antithrombin agents such as heparin, D-phe-pro-arg-chloromethylketone

-7-

(synthetic antithrombin), dipyridamole, hirudin, recombinant hirudin, thrombin inhibitor (available from the Biogen Company), or c7E3 (an antiplatelet drug from the Centocore Company); cytostatic or antiproliferative agents such as angiopeptin (a somatostatin analogue from the Ibsen Company), angiotensin-converting enzyme inhibitors such as Captopril (available from the Squibb Company), Cilazapril (available from the Hoffman-LaRoche Company), or Lisinopril (available from the Merck Company) calcium channel blockers (such as Nifedipine), colchicine, fibroblast growth factor (FGF) antagonists, fish oil (omega 3-fatty acid), low molecular weight heparin (available from the Wyeth and Glycomed Companies), histamine antagonists, Lovastatin (an inhibitor of HMG-CoA reductase, a cholesterol lowering drug from the Merck Company), methotrexate, monoclonal antibodies (such as to PDGF receptors), nitroprusside, phosphodiesterase inhibitors, prostacyclin and prostacyclin analogues, prostaglandin inhibitor (available from the Glaxo Company), Seramin (a PDGF antagonist), serotonin blockers, steroids, thioprotease inhibitors, and triazolopyrimidine (a PDGF antagonist). Other therapeutic drugs which may be appropriate include alpha-interferon and genetically engineered epithelial cells, for example.

The particles of the desired therapeutic drug preferably are formed by air milling of crystals of the therapeutic drug to form microgranules of the therapeutic drug. This method is preferred because it typically produces no heat and generally does not lead to contamination of the therapeutic drug. The particles of the desired therapeutic drug can also be formed by recrystallization, ball milling or grinding, as long as generation of heat and possible contamination are closely controlled.

The particles of the desired therapeutic drug preferably are formed to have a maximum cross-sectional

dimension of about 10 microns. An average particle size of less than 10 microns, and a uniform distribution of the particles of the therapeutic drug in the polymeric material, are critical to provision of a therapeutically effective amount of the therapeutic drug in the layer of polymeric material to be applied to the structure of the stent, because the layer of polymeric material typically can be as thin as 25 microns. The size and distribution of the particles of the therapeutic drug also can affect the physical properties of the polymer.

In a preferred aspect of the method of the invention, the polymeric material in which the therapeutic drug is incorporated has a relatively low processing temperature, such as polycaprolactone, having a processing temperature of approximately 80°C, poly(ethylene-co-vinyl acetate) or poly(vinyl acetate), having processing temperatures of approximately 100°C, or silicone gum rubber, having a processing temperature of about 40°C, for example. Other polymers having similar relatively low processing temperatures also may be suitable. Other polymers which may be suitable include non-degradable polymers capable of carrying and delivering therapeutic drugs, and biodegradable, bioabsorbable polymers capable of carrying and delivering therapeutic drugs, such as poly-DL-lactic acid (DL-PLA), and poly-L-lactic acid (L-PLA), polyorthoesters, polyiminocarbonates, aliphatic polycarbonates, and polyphosphazenes.

Alternatively, the therapeutic drug can be compounded with the polymer by calendaring the ingredients, such as in a two-roll mill, for example. This method also can yield a relatively high and uniformly distributed loading of the therapeutic drug in the polymer.

A porosigen also can be incorporated in the drug-loaded polymer by adding the porosigen to the polymer along with the therapeutic drug to form a porous,

drug-loaded polymeric membrane. A porosigen is defined herein for purposes of this application as any moiety, such as microgranules of sodium chloride, lactose, or sodium heparin, for example, which will dissolve or otherwise will be degraded when immersed in body fluids to leave behind a porous network in the polymeric material. The pores left by such porosigens typically can be as large as 10 microns. The pores formed by porosigens such as polyethylene glycol (PEG), polyethylene oxide/polypropylene oxide (PEO/PPO) copolymers, for example, also can be smaller than one micron, although other similar materials which form phase separations from the continuous drug-loaded polymeric matrix and can later be leached out by body fluids also can be suitable for forming pores smaller than one micron. While currently it is preferred to apply the polymeric material to the structure of a stent during the time that the therapeutic drug and porosigen material are contained within the polymeric material, to allow the porosigen to be dissolved or degraded by body fluids when the stent is placed in a blood vessel, alternatively the porosigen can be dissolved and removed from the polymeric material to form pores in the polymeric material prior to placement of the polymeric material combined with the stent within a blood vessel.

If desired, a rate-controlling membrane also can be applied over the drug-loaded polymer, to limit the release rate of the therapeutic drug. Such a rate-controlling membrane can be useful for delivery of water soluble substances as to which a nonporous polymer film would completely prevent diffusion of the drug. The rate-controlling membrane can be added by applying a coating from a solution, or a lamination, as described previously. The rate-controlling membrane applied over the polymeric material can be formed to include a uniform dispersion of a porosigen in the rate-controlling membrane, and the porosigen in the rate-controlling

5 membrane can be dissolved to leave pores in the rate-controlling membrane typically as large as 10 microns, or as small as 1 micron, for example, although the pores also can be smaller than 1 micron. The porosigen in the rate-controlling membrane can be, for example, sodium chloride, lactose, sodium heparin, polyethylene glycol, polyethylene oxide/polypropylene oxide copolymers, and mixtures thereof.

10 The drug-loaded polymer can be laminated to the surface of a stent. The inner reinforcement structure to which the drug-loaded polymer is laminated preferably is formed from a thin sheet of metal, such as stainless steel, although other metals such as platinum-iridium alloy, molybdenum-rhenium alloy, tantalum, gold, combinations thereof and other similar materials also may
15 be suitable. The inner metal reinforcement structure of the stent preferably is laminated with polymer films on each side, with at least one coating of a polymer film. Alternatively, the reinforcement structure also can be coated on one side, if desired. At least one laminating polymeric film capable of absorbing and releasing therapeutic drugs is placed on at least one side of the reinforcement member of the stent, and the laminating polymeric film is heated to its appropriate processing
20 temperature to bond the laminating polymeric film to the surface of the inner stent member to form a laminated stent member.

25 When the structural reinforcement member 30 of the stent is to be laminated on one side only, the reinforcement member and polymer film can be bonded by a typical two-ply fusion lamination system 32, as is illustrated in Fig. 2. The two-ply laminating stack typically includes an idler roll 34 receiving a sheet of the reinforcement members 30, and a lay-on roll 36
30 receiving the drug-loaded polymeric film 28. The reinforcement member 30 and drug-loaded polymeric film 28 are pressed into intimate contact between the lay-on roll

and the heating and combining drum 38, and can be heated by the drum and take-off heat roll 40, where the reinforcement member and drug-loaded film laminate can be utilized for further processing in making the drug-loaded stent.

When the reinforcement member is to be laminated on both sides, the reinforcement member 30 and drug-loaded polymeric film layers 28, 29 can be bonded together by typical three-ply fusion lamination rolls, as is illustrated in Fig. 3. Such a three-ply fusion lamination system 42 typically can include a first preheat roll system 44 for receiving and preheating one drug-loaded polymeric film 28, a second preheat roll system 46 for receiving and preheating the sheet of reinforcement members 30, and a lay-on roll 48 for pressing the reinforcement member and first drug-loaded polymeric laminating film together in intimate contact against the heating-and-combining drum 50. A third preheat roll system 52 can be provided for receiving and preheating the second drug-loaded polymeric laminating film 29, and a lay-on roll 54 presses the second drug-loaded polymeric laminating film and reinforcement member together in intimate contact against the drum. The reinforcement member and two layers of laminating film can be further heated by the drum and take-off heat roll 56, and removed for further processing in making the drug-loaded stent. Other laminating systems that combine the reinforcement member with one or more of the drug-loaded polymeric laminating films also may be suitable. Alternatively, the polymeric film can be applied by solvent casting, or by adhering the film to the surface of the inner stent member with a biocompatible adhesive.

Any excess polymer extending beyond the desired edges of orifices or the outside edges of the stent preferably is removed, typically by cutting with a laser (not shown), such as a continuous CO₂ laser, a pulsed yttrium aluminum garnet (YAG) laser, or an excimer laser,

-12-

for example, although the excess polymer also can be removed by stamping and the like.

5 It thus has been demonstrated that the invention provides for a polymeric material containing a therapeutically effective amount of a therapeutic drug that can be combined with a reinforcement structure of an intravascular stent, and a method of incorporating the therapeutic drug into the polymeric material for combination with the stent, and for forming the polymeric material as a thin layer containing a therapeutically effective amount of the therapeutic drug to be incorporated in the stent without significantly increasing the thickness of the stent.

10 It will be apparent from the foregoing that while particular forms of the invention have been illustrated and described, various modifications can be made without departing from the scope of the invention. Accordingly, it is not intended that the invention be limited, except as by the appended claims.

WHAT IS CLAIMED IS:

1. A method of incorporating a therapeutically effective amount of a therapeutic drug into a polymeric material for application to an intravascular stent, comprising the steps
5 of:

forming solid particles of a therapeutic drug to have a maximum cross-sectional dimension of about 10 microns;

uniformly dispersing the solid particles of the therapeutic drug in a polymeric material such that the particles of the therapeutic drug form greater than 30% and up to
10 70% by weight of the total weight of the therapeutic drug and the polymeric material;

uniformly dispersing a porosity in the polymeric material together with the therapeutic drug; and

applying the polymeric material to an inner reinforcement structure to form the intravascular stent.

15

2. The method of claim 1, wherein said step of forming solid particles of the therapeutic drug comprises air milling crystals of the therapeutic drug.

3. The method of claim 1, wherein the step of forming solid particles of the
20 therapeutic drug comprises recrystallizing crystals of the therapeutic drug.

4. The method of claim 1, wherein the step of forming solid particles of the therapeutic drug comprises ball milling crystals of the therapeutic drug.

5. The method of claim 1, wherein the step of forming solid particles of the
25 therapeutic drug comprises grinding crystals of the therapeutic drug.

6. The method of claim 1, wherein the therapeutic drug is selected from the group consisting of heparin, D-phe-pro-arg-chloromethylketone, dipyrindamole, hirudin,
30 recombinant hirudin, thrombin inhibitor, angiotensin-converting enzyme inhibitors, calcium channel blockers, colchicine, fibroblast growth factor antagonists, fish

oil, omega 3-fatty acid, low molecular weight heparin, histamine antagonists, inhibitors of HMG-CoA reductase, methotrexate, monoclonal antibodies, nitroprusside, phosphodiesterase inhibitors, prostacyclin and prostacyclin analogues, prostaglandin inhibitor, PDGF antagonists, serotonin blockers, steroids, thioprotease inhibitors, triazolopyrimidine, alpha-interferon, and genetically engineered epithelial cells, and mixtures thereof.

7. The method of any one of claims 1-6, wherein the polymeric material has a relatively low thermal processing temperature.

8. The method of any one of claims 1-6, wherein the polymeric material has a thermal processing temperature of not more than approximately 100°C.

9. The method of any one of claims 1-6, wherein the polymeric material is selected from the group consisting of polycaprolactone, poly(ethylene-co-vinyl acetate), poly(vinyl acetate), silicone gum rubber, poly-DL-lactic acid (DL-PLA), poly-L-lactic acid (L-PLA), polyorthoesters, polyiminocarbonates, aliphatic polycarbonates, polyphosphazenes, and mixtures thereof.

10. The method of any one of claims 1-9, wherein the solid particles of the therapeutic drug comprise greater than 30% and up to 40% by weight of the total weight of the therapeutic drug and the polymeric material.

11. The method of any one of claims 1-10, wherein the step of uniformly dispersing the solid particles of the therapeutic drug in the polymeric material comprises coextruding the particles of the therapeutic drug and the polymeric material.

12. The method of any one of claims 1-10, wherein the step of uniformly dispersing the solid particles of the therapeutic drug in the polymeric material comprises calendaring the particles of the therapeutic drug and the polymeric material together.

13. The method of any one of claims 1-10, wherein the step of uniformly dispersing the solid particles of the therapeutic drug in the polymeric material comprises solvent casting the particles of the therapeutic drug together with the polymeric material.

5 14. The method of any one of claims 1-10, wherein the step of uniformly dispersing a porosigen in the polymeric material together with the therapeutic drug comprises coextruding the porosigen together with the therapeutic drug and the polymeric material.

10 15. The method of claim 14, wherein the step of uniformly dispersing a porosigen in the polymeric material together with the therapeutic drug further includes the step of dissolving the porosigen in the polymeric material to leave pores in the polymeric material.

15 16. The method of claim 15, wherein the pores have a maximum cross-sectional dimension of about 10 microns.

17. The method of claim 15, wherein the pores have a maximum cross-sectional dimension of about one micron.

20

18. The method of any one of claims 1-15, wherein the porosigen is selected from the group consisting of sodium chloride, lactose, sodium heparin, polyethylene glycol, polyethylene oxide/polypropylene oxide copolymers, and mixtures thereof.

25 19. The method of any one of claims 1-18, further including the step of applying a rate-controlling membrane over the polymeric material to control the release rate of the therapeutic drug from the polymeric material.

30 20. The method of claim 19, wherein the step of applying a rate-controlling membrane over the polymeric material comprises forming the rate-controlling membrane to include a uniform dispersion of a porosigen in the rate-controlling membrane.

21. The method of claim 20, wherein the step of applying a rate-controlling membrane over the polymeric material further includes the step of dissolving the porosigen
5 in the rate-controlling membrane to leave pores in the rate-controlling membrane.

22. The method of claim 20, wherein the porosigen in the rate-controlling membrane is selected from the group consisting of sodium chloride, lactose, sodium heparin, polyethylene glycol, polyethylene oxide/polypropylene oxide copolymers, and
10 mixtures thereof.

23. The method of any one of claims 1-22, further including the step of forming the polymeric material containing the therapeutic drug as a sheet at least about 25 microns thick.
15

24. The method of claim 23, wherein the step of applying the polymeric material to the intravascular stent further includes laminating the sheet of polymeric material containing the therapeutic drug to the inner reinforcement structure.

20 25. The method of claim 24, further including the step of removing excess polymeric material laminated to the inner reinforcement structure.

26. An intravascular stent for carrying and delivering a therapeutic drug within a blood vessel in which the intravascular stent is placed, comprising:

25 an inner reinforcement structure;

a polymeric material disposed on the inner reinforcement structure, the polymeric material having a relatively low thermal processing temperature and, uniformly dispersed therein, solid particles of a therapeutic drug, the solid particles of the therapeutic drug comprising greater than 30% and up to 70% by weight of the total weight of the
30 therapeutic drug and the polymeric material; and

a porosigen uniformly dispersed in the polymeric material together with the therapeutic drug.

27. The intravascular stent of claim 26, wherein the polymeric material has a
5 thermal processing temperature no greater than about 100°C.

28. The intravascular stent of claim 26, wherein the polymeric material is selected from the group consisting of polycaprolactone, poly(ethylene-co-vinyl acetate), poly(vinyl acetate), silicone gum rubber, poly-DL-lactic acid (DL-PLA), poly-L-lactic acid
10 (L-PLA), polyorthoesters, polyiminocarbonates, aliphatic polycarbonates, polyphosphazenes, and mixtures thereof.

29. The intravascular stent of any one of claims 26-28, wherein the therapeutic drug is a drug selected from the group consisting of heparin,
15 D-phe-pro-arg-chloromethylketone, dipyridamole, hirudin, recombinant hirudin, thrombin inhibitor, angiopeptin, angiotensin converting enzyme inhibitors, calcium channel blockers, colchicine, fibroblast growth factor antagonists, fish oil, omega 3-fatty acid, low molecular weight heparin, histamine antagonists, inhibitors of HMG-CoA reductase, methotrexate, monoclonal antibodies, nitroprusside, phosphodiesterase inhibitors, prostacyclin and
20 prostacyclin analogues, prostaglandin inhibitor, PDGF antagonists, serotonin blockers, steroids, thioprotease inhibitors, triazolopyrimidine, alpha-interferon, and genetically engineered epithelial cells, and mixtures thereof.

30. The intravascular stent of any one of claims 26-29, wherein the porosigen is
25 selected from the group consisting of sodium chloride, lactose, sodium heparin, polyethylene glycol, polyethylene oxide/polypropylene oxide copolymers, and mixtures thereof.

31. The intravascular stent of any one of claims 26-30, wherein the polymeric
30 material comprises a surface defining pores with a maximum cross-sectional dimension of less than about 10 microns.

32. The intravascular stent of any one of claims 26-31, further including a rate-controlling membrane.

5 33. The intravascular stent of claim 32, wherein the rate-controlling membrane is formed to include a uniform distribution of a porosigen, the porosigen being selected from the group consisting of sodium chloride, lactose, sodium heparin, polyethylene glycol, polyethylene oxide/polypropylene oxide copolymers, and mixtures thereof.

10 34. The intravascular stent of claim 32, wherein the rate-controlling membrane comprises a surface defining pores with a maximum cross-sectional dimension of about ten microns.

15 35. The intravascular stent of claim 32, wherein the rate-controlling membrane comprises a surface defining pores with a maximum cross-sectional dimension of about one micron.

20 36. The intravascular stent of any one of claims 26-35, wherein the polymeric material containing the therapeutic drug is formed as a sheet at least about 25 microns thick.

37. The intravascular stent of claim 36, wherein the sheet of polymeric material containing the therapeutic drug is laminated to the inner reinforcement structure.

38. A polymeric material containing a therapeutic drug for application to an intravascular stent for carrying and delivering said therapeutic drug with a blood vessel in which said intravascular stent is placed, comprising:

5 a polymeric material having a thermal processing temperature no greater than about 100°C;

particles of a therapeutic drug incorporated in said polymeric material; and

a porosigen uniformly dispersed in said polymeric material, said porosigen being selected from the group consisting of sodium chloride, lactose, sodium heparin, polyethylene glycol, copolymers of polyethylene oxide and polypropylene oxide, and
10 mixtures thereof.

39. The polymeric material of claim 38, wherein said polymeric material is selected from the group consisting of polycaprolactone, poly(ethylene-co-vinyl acetate), poly(vinyl acetate), silicone gum rubber, poly-DL-lactic acid (DL-PLA), poly-L-lactic acid
15 (L-PLA), polyorthoesters, polyiminocarbonates, aliphatic polycarbonates, polyphosphazenes, and mixtures thereof.

40. The polymeric material of claim 38 or 39, wherein said particles of said therapeutic drug can have a maximum cross-section dimension of up to 50 microns.

20

41. The polymeric material of claim 38, 39, or 40, wherein said therapeutic drug is a drug selected from the group consisting of heparin, D-phe-pro-arg-chloromethylketone, dipyrindamole, hirudin, recombinant hirudin, thrombin inhibitor, angiotensin converting enzyme inhibitors, calcium channel blockers, colchicine, fibroblast growth
25 factor antagonists, fish oil, omega 3-fatty acid, low molecular weight heparin, histamine antagonists, inhibitors of HMG-CoA reductase, methotrexate, monoclonal antibodies, nitroprusside, phosphodiesterase inhibitors, prostacyclin and prostacyclin analogues, prostaglandin inhibitor, PDGF antagonists, serotonin blockers, steroids, thioprotease inhibitors, triazopyrimidine, alpha-interferon, and genetically engineered epithelial cells,
30 and mixtures thereof.

42. The polymeric material of any one of claims 38-41, wherein said particles of said therapeutic drug comprise up to 70% by weight of the total weight of the therapeutic drug and the polymeric material.

5

43. The polymeric material of any one of claims 38-41, wherein said particles of said therapeutic drug comprise up to 40% by weight of the total weight of the therapeutic drug and the polymeric material.

10

44. The polymeric material of any one of claims 38-43, wherein said polymeric material comprises a surface defining pores with a maximum cross-sectional dimension of less than about 10 microns.

15

45. The polymeric material of any one of claims 38-44, further including a rate-controlling membrane.

20

46. The polymeric material of claim 45, wherein said rate-controlling membrane is formed to include a uniform distribution of a porosigen, said porosigen being selected from the group consisting of sodium chloride, lactose, sodium heparin, polyethylene glycol, polyethylene oxide/polypropylene oxide copolymers, and mixtures thereof.

25

47. The polymeric material of claim 45 or 46, wherein said rate-controlling membrane comprises a surface defining pores with a maximum cross-sectional dimension of about ten microns.

48. The polymeric material of claim 45 or 46, wherein said rate-controlling membrane comprises a surface defining pores with a maximum cross-section dimension of about one micron.

49. The polymeric material of any one of claims 38-48, wherein said polymeric material containing said therapeutic drug is formed as a sheet at least about 25 microns thick.

- 5 50. The polymeric material of claim 49, wherein said sheet of polymeric material containing said therapeutic drug is further laminated to an intravascular stent structure.

